

TDS Technical Data Sheet



Properties	Method	Value	Unit
Thickness		≥ 150	mm
Length		≥ 2000	mm
Width		≥ 1200	mm
Density		30	kg/m ³
Colour			Black
Compressive Strength			
	ISO 7214		
25% strain		80	kPa
50% strain		140	kPa
Tensile Strength	ISO 7214	400	kPa
Tensile elongation	ISO 7214	50	%
Compression set 25% - 22h loading			
	ISO 7214		
Stabilising 30 min		16	%
Stabilising 24 h		3	%
Compression set 50% - 22h loading			
	ISO 7214		
Stabilising 30 min		39	%
Stabilising 24 h		5	%
Tear Strength			
	ISO 8067-B	25	N/cm
Hardness Shore 00			
	ISO 868	60	Shore 00
Water absorbtion			
	DIN 53428	<1	%
Thermal conductivity			
	ISO 8301		
Test temperature 10°C		0.039	W/m-K
Test temperature 23°C		0.040	W/m-K
Service temperature			
	Internal	100	°C
Flammability			
	FMVSS302	<100mm/min	pass

This information is provided as a convenience to customers and reflects the result of internal tests conducted on ARPLANK samples. While all reasonable care has been taken to ensure that this information is accurate as of the date of issue, Special-Plast does not represent, warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information. ARPLANK is a registered trade mark.